

MONODUR POLYESTER STANDARD:

Opening / Open Area %	Mesh Opening Inch	Mesh Count		Thread Diameter		Weight oz/yd2
		Inch	CM	Inch	Micron	
2000/64	0.0787	10.2	4.0	0.0197	500	7.8
1600/61	0.0630	12.4	4.9	0.0169	430	6.3
1400/59	0.0551	14.0	5.5	0.0169	430	7.0
1250/60	0.0492	15.7	6.2	0.0146	370	6.2
1000/58	0.0394	18.5	7.3	0.0118	300	4.4
900/52	0.0354	20.3	8.0	0.0118	300	5.0
800/57	0.0315	23.9	9.4	0.0106	270	5.0
710/52	0.0280	25.9	10.2	0.0106	270	5.5
630/49	0.0248	28.2	11.1	0.0106	270	5.3
560/57	0.0220	34.3	13.5	0.0085	215	4.7
500/47	0.0197	35.6	14.0	0.0091	230	5.1
400/43	0.0157	41.7	16.4	0.0085	215	4.4
355/48	0.0140	49.3	19.4	0.0063	160	3.1
315/46	0.0124	53.3	21.0	0.0063	160	3.4
280/50	0.0110	62.0	24.4	0.0051	130	2.4
265/49	0.0104	63.5	25.0	0.0051	130	2.4
250/48	0.0098	66.8	26.3	0.0051	130	2.4
224/44	0.0088	77.2	30.4	0.0051	130	2.8
200/45	0.0079	83.3	32.8	0.0041	105	2.2
180/44	0.0071	94.0	37.0	0.0035	90	2.1
160/45	0.0063	107	42.0	0.0031	80	1.8
140/40	0.0055	114	45.0	0.0031	80	2.0
130/39	0.0051	122	48.0	0.0031	80	2.1
125/38	0.0049	124	49.0	0.0031	80	2.1
118/43	0.0046	142	56.0	0.0024	60	1.5
112/45	0.0044	152	60.0	0.0024	60	1.7
105/52	0.0041	175	69.0	0.0016	40	1.0
100/31	0.0039	142	56.0	0.0028	70	1.9
90/37	0.0035	173	68.0	0.0022	55	1.4
80/38	0.0031	196	77.0	0.0019	48	1.2
71/41	0.0028	229	90.0	0.0016	40	1.1
63/37	0.0025	234	92.0	0.0016	40	1.2
60/36	0.0024	254	100.0	0.0016	40	1.2
56/38	0.0022	279	110.0	0.0014	35	1.0
50/36	0.0020	305	120.0	0.0014	35	1.0
40/28	0.0016	338	133.0	0.0014	35	1.2
35.5/25	0.0014	361	142.0	0.0014	35	1.2
30/25	0.0012	419	165.0	0.0012	30	1.2
22.4/16	0.0009	457	180.0	0.0012	30	1.3
20/15	0.0008	470	185.0	0.0012	30	1.3